

**Product Texts**

LNP LUBRICOMP RAL229 compound is based on Nylon 6/6 resin containing 10% aramid fiber, 10% PTFE. Added features of this grade include: Flame Retardant, Wear Resistant.

UL Yellow Card Link [E121562-101282579](https://www.ul.com/yellowcard/E121562-101282579)

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Break	81	MPa	ASTM D 638
Elongation at Break	4	%	ASTM D 638
Flexural Modulus	3720	MPa	ASTM D 790
Izod Impact notched, 1/8 in	37	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
<b>ASTM Data</b>			
DTUL @ 264 psi	162	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1420	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.25	%	-
Melt temperature	275 - 290	°C	-
Mold temperature	80 - 95	°C	-
Zone 1	265 - 275	°C	-
Zone 2	280 - 295	°C	-
Zone 3	295 - 305	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

**Characteristics****Processing**

Injection Molding

**Additives**

Flame retarding agent

**Special Characteristics**

Flame retardant

**Regional Availability**

North America, Europe, Asia Pacific