

**AKROMID® A3 ICF 10 TM black (7431)**

(PA66+PTFE)-CF10

Akro-Plastic GmbH

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>9000 / 6500</b>	MPa	ISO 527
Stress at break	<b>130 / 90</b>	MPa	ISO 527
Strain at break	<b>3 / 5</b>	%	ISO 527
Charpy impact strength, +23°C	<b>25 / 50</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>3 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eA

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>260 / *</b>	°C	ISO 11357-1/-3
Burning behav. at 1.5 mm nom. thickn. Thickness tested	<b>HB / *</b> <b>1.6 / *</b>	class mm	IEC 60695-11-10 -

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1320 / -</b>	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Melt temperature	<b>320</b>	°C	-
Mold temperature	<b>100</b>	°C	-
Injection pressure	<b>75</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Black

**Additives**

Lubricants

**Features**

Tribologic Grade

**Regional Availability**

Europe, Asia Pacific