

**Product Texts**

Base Polymer	Polycarbonate
Filler/Additive System	special filler
Special Features	light scattering,high light transmission,easy flow,UV stabilised
Market Segment	Automotive,Lighting
Application Area	lighting,light transparent components
Typical Applications	lamp covers,display elements,operating elements

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	30	cm <sup>3</sup> /10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	2400	MPa	ISO 527
<sup>[C]</sup> Yield stress	66	MPa	ISO 527
<sup>[C]</sup> Yield strain	6	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	10	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	128	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	142	°C	ISO 306
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
<sup>[C]</sup> Burning Behav. at thickness h	V-2	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Density	1190	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Features**

Light Diffusing

**Special Characteristics**

U.V. stabilized or stable to weather

**Regional Availability**

North America, Europe, Asia Pacific, Near East/Africa

**Other text information****Injection molding**

Pre-Drying Conditions      120 °C in a dry air (dessiccant) dryer  
    for 2-4 h  
    120 °C in an air circulating dryer  
    for 4-12 h  
    max. moisture content <0,02 %

Processing Injection Moulding      melt temperature 270-310 °C  
    mould temperature 80-110 °C

Storage

dry, protected from light