

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	2500	MPa	ISO 527
Stress at break	64	MPa	ISO 527
Strain at break	>50	%	ISO 527
Izod notched impact strength, +23°C	40	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	15	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-30	°C	-

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	140	°C	ISO 75-1/-2
Vicat softening temperature, B	148	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-2	class	IEC 60695-11-10
Thickness tested	1.6	mm	-

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Comparative tracking index	250	-	IEC 60112

Other properties	Value	Unit	Test Standard
Density	1200	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Regional Availability

Europe