

Product Texts

Base Polymer	Polycarbonate
Special Features	UV stabilised,easy release (demoulding),impact modified
Market Segment	Lighting,electrical and electronic,various
Application Area	lighting,fixtures / fittings,various
Typical Applications	housings,lamps,various

Processing/Physical Characteristics

	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	20	cm ³ /10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-

[C]: CAMPUS

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2300	MPa	ISO 527
^[C] Yield stress	60	MPa	ISO 527
^[C] Yield strain	6	%	ISO 527
^[C] Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	13	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties

	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	120	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	144	°C	ISO 306
^[C] Burning Behav. at 1.5 mm nom. thickn.	V-2	class	IEC 60695-11-10
Thickness tested	1.5	mm	-

[C]: CAMPUS

Other properties

	Value	Unit	Test Standard
^[C] Density	1200	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Applications

Electrical and Electronical

Delivery form

White

Regional Availability

North America, Europe, Asia Pacific, Near East/Africa

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather

Other text information**Injection molding**

Pre-Drying Conditions 120 °C in a dry air (dessiccant) dryer
for 2-4 h
120 °C in an air circulating dryer
for 4-12 h
max. moisture content <0,02 %

Processing Injection Moulding melt temperature 270-310 °C
mould temperature 80-110 °C

Storage

dry, protected from light