

**Product Texts**

Base Polymer	Polycarbonate
Special Features	injection moulding grade, low viscosity
Typical Applications	various

**Processing/Physical Characteristics**

	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	33	cm <sup>3</sup> /10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-

[C]: CAMPUS

**Mechanical properties**

	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	2400	MPa	ISO 527
<sup>[C]</sup> Yield stress	63	MPa	ISO 527
<sup>[C]</sup> Yield strain	20	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	11	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

**Thermal properties**

	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	128	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	143	°C	ISO 306

[C]: CAMPUS

**Other properties**

	Value	Unit	Test Standard
<sup>[C]</sup> Density	1190	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America, Europe, Asia Pacific, Near East/Africa

**Other text information****Injection molding**

Pre-Drying Conditions	in an air circulating dryer 100-120 °C for 4-12 h 120 °C in a dry air (dessiccant) dryer for 3-4 h dependant on moisture content max. moisture content <0,02 %
Processing Injection Moulding	melt temperature 270-310 °C mould temperature 80-110 °C
Storage	dry, protected from light