

**Product Texts**

PA610/ABS blend, 15% glass fibre injection moulding grade. Natural colour.

Suitable for parts requiring improved stiffness and very low moisture absorption. Excellent aesthetic surface aspect.

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>4750 / 4000</b>	MPa	ISO 527
<sup>[C]</sup> Yield stress	<b>90 / 73</b>	MPa	ISO 527
<sup>[C]</sup> Yield strain	<b>4 / 5</b>	%	ISO 527
<sup>[C]</sup> Nominal strain at break	<b>5 / 7.5</b>	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	<b>67 / 65</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>11 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	<b>10 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>220 / *</b>	°C	ISO 11357-1/-3

[C]: CAMPUS

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Water absorption	<b>2.1 / *</b>	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	<b>0.8 / *</b>	%	Sim. to ISO 62
<sup>[C]</sup> Density	<b>1150 / -</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

**Processing**

Injection Molding

**Special Characteristics**

Platable

**Delivery form**

Granules, Natural Color

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

**Additives**

Release agent

**Other text information**

**Injection molding**

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.15%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more. Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

**Injection Molding Processing Parameters**

Melt Temperature	Mold Temperature	Injection Speed
240 - 260°C	40 - 60°C	medium