

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	20	cm ³ /10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	2100	MPa	ISO 527
Yield stress	60	MPa	ISO 527
Yield strain	5	%	ISO 527
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	9	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Glass transition temperature, 10°C/min	148	°C	ISO 11357-1/-2
Temp. of deflection under load, 1.80 MPa	123	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	134	°C	ISO 75-1/-2
Vicat softening temperature, B	140	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-2	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Other properties			
Water absorption	0.35	%	Sim. to ISO 62
Humidity absorption	0.15	%	Sim. to ISO 62
Density	1200	kg/m ³	ISO 1183

Characteristics**Delivery form**

Black

Regional Availability

Europe