

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	3060 / -	MPa	ISO 527
^[C] Stress at break	52 / -	MPa	ISO 527
^[C] Strain at break	18 / -	%	ISO 527
^[C] Charpy notched impact strength, +23°C	6 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	221 / *	°C	ISO 11357-1/-3

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1100 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding, Pipe/Tube Extrusion

Delivery form

Black

Special Characteristics

Heat stabilized or stable to heat

Chemical Resistance

General Chemical Resistance

Certifications

Contains renewable resources

Applications

Automotive