

BESTPOLUX PCU /01

PC

Grupo Triesa

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	22	g/10min	ISO 1133
Mechanical properties			
ISO Data			
Tensile Modulus	2300	MPa	ISO 527
Tensile Strength	66	MPa	ISO 527
Strain at break	>50	%	ISO 527
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	20	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	135	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	140	°C	ISO 75-1/-2
Burning behav. at thickness h	V-2	class	IEC 60695-11-10
Electrical properties			
ISO Data			
Surface resistivity	1E15	Ohm	IEC 62631-3-2
Electric strength	18	kV/mm	IEC 60243-1
Comparative tracking index	250	-	IEC 60112
Other properties			
Water absorption	0.24	%	Sim. to ISO 62
Density	1200	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Natural Color

Additives

Lubricants

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

Europe