

RTP 200 B TFE 15

(PA610+PTFE)

RTP Company

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|--------------|-------------|----------------------|
| ASTM Data | | | |
| Mold Shrinkage, MD | 0.025 | mm/mm | ASTM D 955 |

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Tensile Modulus | 2137 | MPa | ASTM D 638 |
| Tensile Strength | 51.7 | MPa | ASTM D 638 |
| Flexural Modulus | 2068 | MPa | ASTM D 790 |
| Flexural Strength | 72.4 | MPa | ASTM D 790 |
| Izod Impact notched, 1/8 in | 80.1 | J/m | ASTM D 256 |

| Thermal properties | Value | Unit | Test Standard |
|---------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| UL 94 Flame rating | HB | - | UL 94 |
| Thickness tested | 1.59 | mm | - |
| DTUL @ 264 psi | 60 | °C | ASTM D 648 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1170 | kg/m ³ | ASTM D 792 |
| Moisture Content | 0.2 | % | - |

| Processing Recommendation Injection Molding | Value | Unit | Test Standard |
|--|-------------------|-------------|----------------------|
| Pre-drying - Temperature | 79.4 | °C | - |
| Pre-drying - Time | 2 | h | - |
| Melt temperature | 277 - 299 | °C | - |
| Mold temperature | 65.6 - 107 | °C | - |
| Injection pressure | 68.9 - 103 | MPa | - |

Characteristics**Processing**

Injection Molding

Additives

Lubricants

Regional Availability

North America, Europe, Asia Pacific