

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	2300	MPa	ISO 527
Yield stress	60	MPa	ISO 527
Yield strain	6	%	ISO 527
Stress at break	66	MPa	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	2400	MPa	ISO 178
Charpy notched impact strength, +23°C	20	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	83	kJ/m <sup>2</sup>	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	122	°C	ISO 75-1/-2
Vicat softening temperature, B	147	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-2	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3.2	mm	-

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Comparative tracking index	250	-	IEC 60112

Other properties	Value	Unit	Test Standard
Density	1200	kg/m <sup>3</sup>	ISO 1183

**Characteristics**

**Additives**

Release agent

**Regional Availability**

North America, South and Central America

**Applications**

Electrical and Electronical