

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	20	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	64.8	MPa	ASTM D 638
Tensile Strength at Break	70.3	MPa	ASTM D 638
Elongation at Yield	6	%	ASTM D 638
Elongation at Break	120	%	ASTM D 638
Flexural Modulus	2344	MPa	ASTM D 790
Flexural Strength	96.5	MPa	ASTM D 790
Rockwell Hardness	M70	-	ASTM D 785
Izod Impact notched, 1/8 in	747	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 264 psi	127	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	0.15	%	ASTM D 570
Density	1200	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	121	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	271 - 293	°C	-
Mold temperature	71.1 - 93.3	°C	-
Zone 1	249 - 271	°C	-
Zone 2	260 - 282	°C	-
Zone 3	271 - 293	°C	-
Nozzle temperature	266 - 288	°C	-
Screw speed	40 - 70	rpm	-
Back pressure	0.345 - 0.689	MPa	-

## Characteristics

### Processing

Injection Molding

### Features

Low Odor

### Delivery form

Pellets

### Regional Availability

North America