

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	11	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	62.1	MPa	ASTM D 638
Tensile Strength at Break	65.5	MPa	ASTM D 638
Elongation at Yield	7	%	ASTM D 638
Elongation at Break	110	%	ASTM D 638
Flexural Modulus	2340	MPa	ASTM D 790
Rockwell Hardness	R118	-	ASTM D 785
Taber Abrasion Resistance	10	mg/1000 cycles	ASTM D 1044
Izod Impact notched, 1/8 in	800	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	3200	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
DTUL @ 66 psi	138	°C	ASTM D 648
DTUL @ 264 psi	132	°C	ASTM D 648
Vicat Temperature	154	°C	ASTM D 1525
Thermal Conductivity, solid state	0.0274	W/(m K)	ASTM C 177
Specific Heat	1260	J/(kg K)	ASTM C 351
Optical properties			
ASTM Data			
Haze	1	%	ASTM D 1003
Light Transmittance	88	%	ASTM D 1003
Index of Refraction	1.59	-	ASTM D 542
Other properties			
Water Absorption, 24hr	0.15	%	ASTM D 570
Water Absorption, Equilibrium	0.35	%	ASTM D 570
Density	1200	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Pellets

Regional Availability

North America

Special Characteristics

U.V. stabilized or stable to weather, Transparent