EMERGE™ PC 8130-15

PC — Trinseo

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	**15**	g/10min	ISO 1133
Temperature	**300**	°C	-
Load	**1.2**	kg	-
Molding shrinkage, parallel	**0.6**	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	**2400**	MPa	ISO 527
Yield stress	**62**	MPa	ISO 527
Stress at break	**60**	MPa	ISO 527
Strain at break	**110**	%	ISO 527
Flexural modulus, 23°C	**2350**	MPa	ISO 178
Flexural strength	**95**	MPa	ISO 178
Charpy notched impact strength, +23°C	**25**	kJ/m²	ISO 179/1eA
Izod notched impact strength, +23°C	**65**	kJ/m²	ISO 180/1A
Rockwell hardness	**M 73**	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	**123**	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	**142**[ann.]	°C	ISO 75-1/-2
Vicat softening temperature, B	**146**	°C	ISO 306
Coeff. of linear therm. expansion, parallel	**70**	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	**V-0**	class	IEC 60695-11-10
Thickness tested	**1.0**	mm	-
Burning behav. 5V at thickness h	**5VA**	class	IEC 60695-11-20
Thickness tested	**3.0**	mm	-
Oxygen index	**40**	%	ISO 4589-1/-2
Glow Wire Flammability Index (GWFI)	**960**	°C	IEC 60695-2-12
GWFI - thickness tested (1)	**1**	mm	-
Glow Wire Flammability Index (GWFI)	**960**	°C	IEC 60695-2-12
GWFI - thickness tested (2)	**2**	mm	-
Glow Wire Flammability Index (GWFI)	**960**	°C	IEC 60695-2-12
GWFI - thickness tested (3)	**3**	mm	-
Glow Wire Ignition Temperature (GWIT)	**850**	°C	IEC 60695-2-13
GWIT - thickness tested (1)	**1**	mm	-
Glow Wire Ignition Temperature (GWIT)	**850**	°C	IEC 60695-2-13
GWIT - thickness tested (2)	**2**	mm	-
Glow Wire Ignition Temperature (GWIT)	**850**	°C	IEC 60695-2-13
GWIT - thickness tested (3)	**3**	mm	-

ann.: annealed

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	**>1E13**	Ohm*m	IEC 62631-3-1
Surface resistivity	**>1E15**	Ohm	IEC 62631-3-2
Electric strength	**17**	kV/mm	IEC 60243-1
Comparative tracking index	**225**	-	IEC 60112

Other properties	Value	Unit	Test Standard
Density	**1200**	kg/m³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	**120**	°C	-
Pre-drying - Time	**3 - 4**	h	-

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.

Melt temperature	**260 - 300**	°C	-
Mold temperature	**70 - 100**	°C	-

Characteristics

Processing
Injection Molding

Additives
Release agent

Special Characteristics
Flame retardant, Phosphorus-free, U.V. stabilized or stable to weather, Heat stabilized or stable to heat, Opaque

Applications
Electrical and Electronical

Regional Availability
North America, Europe, Near East/Africa

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.