

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577
Mechanical properties			
Value	Unit	Test Standard	
ISO Data			
Tensile Modulus	2400	MPa	ISO 527
Yield stress	60	MPa	ISO 527
Yield strain	6	%	ISO 527
Stress at break	70	MPa	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	2350	MPa	ISO 178
Charpy notched impact strength, +23°C	25	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	65	kJ/m ²	ISO 180/1A
Thermal properties			
Value	Unit	Test Standard	
ISO Data			
Temp. of deflection under load, 1.80 MPa	124	°C	ISO 75-1/-2
Vicat softening temperature, B	148	°C	ISO 306
Coeff. of linear therm. expansion, parallel	70	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-2	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	1.8	mm	-
Oxygen index	40	%	ISO 4589-1/-2
Electrical properties			
Value	Unit	Test Standard	
ISO Data			
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	17	kV/mm	IEC 60243-1
Comparative tracking index	225	-	IEC 60112
Optical properties			
Value	Unit	Test Standard	
ASTM Data			
Light Transmittance	89	%	ASTM D 1003
Other properties			
Value	Unit	Test Standard	
Density	1200	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Value	Unit	Test Standard	
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	≥300	°C	-
Mold temperature	70 - 100	°C	-

Characteristics

Processing

Injection Molding

Additives

Release agent

Applications

IT / Business Machine, Electrical and Electronical, Encapsulation

Regional Availability

Europe, Near East/Africa

Special Characteristics

Flame retardant, Phosphorus-free, Heat stabilized or stable to heat, Transparent