

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	7	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2206	MPa	ASTM D 638
Tensile Strength at Yield	60	MPa	ASTM D 638
Tensile Strength at Break	57.9	MPa	ASTM D 638
Elongation at Yield	6.2	%	ASTM D 638
Elongation at Break	110	%	ASTM D 638
Flexural Modulus	2399	MPa	ASTM D 790
Flexural Strength	93.8	MPa	ASTM D 790
Rockwell Hardness	R 123	-	ASTM D 785
Izod Impact notched, 1/8 in	747	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.5	mm	-
Coefficient of Thermal Expansion, MD	64.8	E-6/K	ASTM D 696
DTUL @ 66 psi	139	°C	ASTM D 648
DTUL @ 264 psi	127	°C	ASTM D 648
Vicat Temperature	149	°C	ASTM D 1525
Limiting Oxygen Index	35	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1200	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	121	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	271 - 288	°C	-
Mold temperature	65.6 - 98.9	°C	-

Characteristics

Processing

Injection Molding

Special Characteristics

Flame retardant, Phosphorus-free

Applications

IT / Business Machine, Electrical and Electronical

Regional Availability

Asia Pacific