

**Gebalon PC ULtimate G0 FR**

PC

geba Kunststoffcompounds GmbH

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>2200</b>	MPa	ISO 527
Yield stress	<b>60</b>	MPa	ISO 527
Yield strain	<b>6.2</b>	%	ISO 527
Charpy impact strength, +23°C	<b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eU

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>124</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	<b>136</b>	°C	ISO 75-1/-2
Vicat softening temperature, B	<b>141</b>	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	<b>V-0</b>	class	IEC 60695-11-10
Thickness tested	<b>1.5</b>	mm	-
Burning behav. at thickness h	<b>V-0</b>	class	IEC 60695-11-10
Thickness tested	<b>3.0</b>	mm	-

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1200</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding

**Delivery form**

Granules

**Special Characteristics**

Flame retardant, High impact or impact modified, U.V. stabilized or stable to weather

**Chemical Resistance**

General Chemical Resistance

**Applications**

Electrical and Electronical

**Regional Availability**

North America, Europe