

RTP 282 D TFE 15
(PA612+PTFE)-CF15

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.002	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	12410	MPa	ASTM D 638
Tensile Strength	162	MPa	ASTM D 638
Flexural Modulus	10690	MPa	ASTM D 790
Flexural Strength	224	MPa	ASTM D 790
Izod Impact notched, 1/8 in	69.4	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.59	mm	-

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Volume Resistivity	10000	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1240	kg/m ³	ASTM D 792
Moisture Content	0.2	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	79.4	°C	-
Pre-drying - Time	4	h	-
Melt temperature	249 - 285	°C	-
Mold temperature	60 - 93.3	°C	-
Injection pressure	68.9 - 124	MPa	-

Characteristics

Processing
Injection Molding

Regional Availability
North America, Europe, Asia Pacific

Additives
Lubricants