

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	11	g/10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
Molding shrinkage, parallel	0.7	%	ISO 294-4, 2577
Molding shrinkage, normal	0.8	%	ISO 294-4, 2577
ASTM Data			
Melt Flow Index, MFI	11	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.0065	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.0075	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2100	MPa	ISO 527
Yield stress	62	MPa	ISO 527
Stress at break	64	MPa	ISO 527
Strain at break	91	%	ISO 527
Flexural modulus, 23°C	2200	MPa	ISO 178
Flexural strength	91	MPa	ISO 178
Charpy notched impact strength, +23°C	78	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	69	kJ/m ²	ISO 180/1A
Rockwell hardness	R 122	-	ISO 2039-2
ASTM Data			
Tensile Modulus	2200	MPa	ASTM D 638
Tensile Strength at Yield	63	MPa	ASTM D 638
Tensile Strength at Break	65	MPa	ASTM D 638
Elongation at Break	110	%	ASTM D 638
Flexural Modulus	2300	MPa	ASTM D 790
Flexural Strength	90	MPa	ASTM D 790
Rockwell Hardness	R 122	-	ASTM D 785
Izod Impact notched, 1/8 in	850	J/m	ASTM D 256
Izod Impact notched, 1/4 in	150	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	124	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	137	°C	ISO 75-1/-2
Vicat softening temperature, B	144	°C	ISO 306
ASTM Data			
DTUL @ 264 psi	135	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1190	kg/m ³	ISO 1183
Density	1190	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.05	%	-
Melt temperature	270 - 290	°C	-
Mold temperature	50 - 60	°C	-
Zone 1	260 - 270	°C	-
Zone 2	270 - 280	°C	-
Zone 3	285 - 295	°C	-
Nozzle temperature	290	°C	-

INFINO LT-1100

PC

Lotte Chemical Corporation

Screw speed	60 - 80	rpm	-
Injection pressure	7.8	MPa	-
Back pressure	3.9 - 5.9	MPa	-

Characteristics**Processing**

Injection Molding

Applications

Automotive

Delivery form

Pellets, Natural Color

Regional Availability

North America, Europe, Asia Pacific