

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	20	g/10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577
ASTM Data			
Melt Flow Index, MFI	20	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.006	mm/mm	ASTM D 955
Mechanical properties			
ISO Data	Value	Unit	Test Standard
Tensile Modulus	2000	MPa	ISO 527
Yield stress	65	MPa	ISO 527
Stress at break	65	MPa	ISO 527
Strain at break	90	%	ISO 527
Flexural modulus, 23°C	2050	MPa	ISO 178
Flexural strength	90	MPa	ISO 178
Charpy notched impact strength, +23°C	25	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	45	kJ/m ²	ISO 180/1A
Rockwell hardness	R 120	-	ISO 2039-2
ASTM Data			
Tensile Modulus	2100	MPa	ASTM D 638
Tensile Strength at Yield	64	MPa	ASTM D 638
Tensile Strength at Break	64	MPa	ASTM D 638
Elongation at Break	65	%	ASTM D 638
Flexural Modulus	2300	MPa	ASTM D 790
Flexural Strength	97	MPa	ASTM D 790
Rockwell Hardness	R 120	-	ASTM D 785
Izod Impact notched, 1/8 in	690	J/m	ASTM D 256
Izod Impact notched, 1/4 in	120	J/m	ASTM D 256
Thermal properties			
ISO Data	Value	Unit	Test Standard
Temp. of deflection under load, 1.80 MPa	120	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	130	°C	ISO 75-1/-2
Vicat softening temperature, B	138	°C	ISO 306
Burning behav. at thickness h	V-2	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
ASTM Data			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	0.75	mm	-
DTUL @ 66 psi	130	°C	ASTM D 648
DTUL @ 264 psi	120	°C	ASTM D 648
Electrical properties			
ISO Data	Value	Unit	Test Standard
Comparative tracking index	212	-	IEC 60112
Other properties			
Value	Unit	Test Standard	
Density	1200	kg/m ³	ISO 1183
Density	1200	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	100	°C	-
Pre-drying - Time	4 - 6	h	-
Processing humidity	≤0.04	%	-
Melt temperature	280	°C	-
Mold temperature	80 - 110	°C	-
Zone 1	250 - 260	°C	-
Zone 2	260 - 270	°C	-
Zone 3	270 - 280	°C	-
Nozzle temperature	280	°C	-
Screw speed	30 - 50	rpm	-
Injection pressure	98	MPa	-
Back pressure	1 - 2	MPa	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Delivery form

Pellets, Natural Color