

**LNP™ LUBRICOMP™ Compound IFL21 - Asia**

(PA612+PTFE)-GF5

Saudi Basic Industries Corporation (SABIC)

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Modulus	<b>3620</b>	MPa	ASTM D 638
Tensile Strength at Break	<b>70</b>	MPa	ASTM D 638
Elongation at Break	<b>2.8</b>	%	ASTM D 638
Flexural Modulus	<b>3330</b>	MPa	ASTM D 790
Flexural Strength	<b>110</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>30</b>	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	<b>270</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
DTUL @ 264 psi	<b>183</b>	°C	ASTM D 648

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1170</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Regional Availability**

Asia Pacific