

RTP 201 D TFE 5
(PA612+PTFE)-GF10

RTP Company

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|--------------|-------------|----------------------|
| ASTM Data | | | |
| Mold Shrinkage, MD | 0.007 | mm/mm | ASTM D 955 |

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Tensile Modulus | 4137 | MPa | ASTM D 638 |
| Tensile Strength | 75.8 | MPa | ASTM D 638 |
| Flexural Modulus | 3792 | MPa | ASTM D 790 |
| Flexural Strength | 121 | MPa | ASTM D 790 |
| Izod Impact notched, 1/8 in | 48 | J/m | ASTM D 256 |

| Thermal properties | Value | Unit | Test Standard |
|---------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| UL 94 Flame rating | HB | - | UL 94 |
| Thickness tested | 1.59 | mm | - |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1140 | kg/m ³ | ASTM D 792 |
| Moisture Content | 0.2 | % | - |

| Processing Recommendation Injection Molding | Value | Unit | Test Standard |
|--|-------------------|-------------|----------------------|
| Pre-drying - Temperature | 79.4 | °C | - |
| Pre-drying - Time | 4 | h | - |
| Melt temperature | 249 - 285 | °C | - |
| Mold temperature | 60 - 93.3 | °C | - |
| Injection pressure | 68.9 - 124 | MPa | - |

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Additives

Lubricants