

Product Texts

LNP LUBRICOMP IFL34 compound is based on Nylon 6/12 resin containing 20% glass fiber, 15% PTFE. Added features of this grade include: Wear Resistant.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.4	%	ISO 294-4, 2577
Molding shrinkage, normal	1.1	%	ISO 294-4, 2577
ASTM Data			
Mold Shrinkage, MD	0.4	mm/mm	ASTM D 955
Mold Shrinkage, TD	1.1	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	7100	MPa	ISO 527
Yield stress	121	MPa	ISO 527
Yield strain	3	%	ISO 527
Stress at break	121	MPa	ISO 527
Strain at break	3	%	ISO 527
Flexural modulus	6100	MPa	ISO 178
Flexural strength	176	MPa	ISO 178
Izod impact strength, +23°C, 4mm	53	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	9	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	6890	MPa	ASTM D 638
Tensile Strength at Yield	115	MPa	ASTM D 638
Tensile Strength at Break	115	MPa	ASTM D 638
Elongation at Yield	3.1	%	ASTM D 638
Elongation at Break	3.1	%	ASTM D 638
Flexural Modulus	5510	MPa	ASTM D 790
Flexural Strength	172	MPa	ASTM D 790
Izod Impact notched, 1/8 in	96	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	929	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	195	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	212	°C	ISO 75-1/-2
ASTM Data			
DTUL @ 66 psi	212	°C	ASTM D 648
DTUL @ 264 psi	197	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1350	kg/m ³	ISO 1183
Water Absorption, 24hr	0.1	%	ASTM D 570
Density	1350	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.2	%	-
Melt temperature	270 - 275	°C	-
Mold temperature	65 - 95	°C	-
Zone 1	255 - 265	°C	-
Zone 2	260 - 270	°C	-
Zone 3	270 - 280	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific