

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>30</b>	g/10min	ASTM D 1238
Temperature	<b>300</b>	°C	-
Load	<b>1.2</b>	kg	-
Mold Shrinkage, MD	<b>0.0065</b>	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength	<b>61.4</b>	MPa	ASTM D 638
Flexural Modulus	<b>2482</b>	MPa	ASTM D 790
Flexural Strength	<b>103</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 120</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>747</b>	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-2</b>	-	UL 94
Thickness tested	<b>0.8</b>	mm	-
DTUL @ 264 psi	<b>110</b>	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	<b>1180</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Special Characteristics**

Flame retardant, Halogen-free

**Certifications**

RoHS compliant

**Applications**

Electrical and Electronical

**Regional Availability**

Europe, Asia Pacific