

KOPHOS® KO1365

PC

Kolon Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	11	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength	69	MPa	ASTM D 638
Flexural Modulus	2452	MPa	ASTM D 790
Flexural Strength	108	MPa	ASTM D 790
Izod Impact notched, 1/8 in	834	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	0.8	mm	-
DTUL @ 264 psi	134	°C	ASTM D 648
Optical properties			
ISO Data			
Haze	99	-	ISO 14782
Other properties			
Density	1200	kg/m ³	ASTM D 792

Characteristics**Features**

Light Diffusing

Regional Availability

North America, Asia Pacific