

**Kotex K-20MRA**

PC

Kotec Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	20	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Break	63	MPa	ASTM D 638
Elongation at Break	120	%	ASTM D 638
Flexural Modulus	2160	MPa	ASTM D 790
Flexural Strength	85	MPa	ASTM D 790
Izod Impact notched, 1/8 in	740	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	0.4	mm	-
DTUL @ 264 psi	131	°C	ASTM D 648

Electrical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Dielectric Strength, Short Time	20	kV/mm	ASTM D 149
Dissipation Factor, 1 MHz	0.009	-	ASTM D 150
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257
Arc Resistance	110	s	ASTM D 495

Optical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Haze	1	%	ASTM D 1003
Light Transmittance	89	%	ASTM D 1003
Index of Refraction	1.58	-	ASTM D 542

Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	0.2	%	ASTM D 570
Density	1200	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets

**Features**

Low Odor, Non Blooming

**Applications**

General Purpose

**Regional Availability**

North America, Europe, Near East/Africa