

**Product Texts**

11 MFR LEXAN High Flow Ductile Copolymer UV stabilized, available in transparent colors only

UL Yellow Card Link [E207780-100988260](https://www.ul.com/lexan-hfd1433)

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	10	cm <sup>3</sup> /10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
<b>ASTM Data</b>			
Melt Flow Index, MFI	11	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	2120	MPa	ISO 527
Yield stress	61	MPa	ISO 527
Yield strain	6	%	ISO 527
Stress at break	68	MPa	ISO 527
Strain at break	50	%	ISO 527
Flexural modulus	2090	MPa	ISO 178
Charpy impact strength, +23°C, 3mm	N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C, 3mm	N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C, 3mm	80	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C, 3mm	43	kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C, 3mm	70	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength, -30°C, 3mm	32	kJ/m <sup>2</sup>	ISO 180/1A
<b>ASTM Data</b>			
Tensile Modulus	2240	MPa	ASTM D 638
Tensile Strength at Yield	58	MPa	ASTM D 638
Tensile Strength at Break	67	MPa	ASTM D 638
Elongation at Yield	6	%	ASTM D 638
Elongation at Break	137	%	ASTM D 638
Flexural Modulus	2230	MPa	ASTM D 790
Rockwell Hardness	R 120	-	ASTM D 785
Izod Impact notched, 1/8 in	903	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	435	J/m	ASTM D 256
Temperature	-30	°C	-

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	115	°C	ISO 75-1/-2
Vicat softening temperature, B	130	°C	ISO 306
Vicat softening temperature, 120°C/h 50N	131	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
<b>ASTM Data</b>			
DTUL @ 66 psi	124	°C	ASTM D 648
DTUL @ 264 psi	114	°C	ASTM D 648
Vicat Temperature	136	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Water absorption	0.3	%	Sim. to ISO 62
Humidity absorption	0.15	%	Sim. to ISO 62
Density	1200	kg/m <sup>3</sup>	ISO 1183
Density	1200	kg/m <sup>3</sup>	ASTM D 792

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>105 - 110</b>	°C	-
Pre-drying - Time	<b>3 - 4</b>	h	-
Melt temperature	<b>260 - 305</b>	°C	-
Mold temperature	<b>50 - 80</b>	°C	-
Zone 1	<b>240 - 280</b>	°C	-
Zone 2	<b>250 - 295</b>	°C	-
Zone 3	<b>260 - 305</b>	°C	-
Screw speed	<b>35 - 75</b>	rpm	-
Back pressure	<b>0.3 - 0.7</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Regional Availability**

Asia Pacific

**Special Characteristics**

Transparent