

**Product Texts**

XHT3143T is a high flow, UV stabilized, high heat polycarbonate copolymer. It is only available in limited transparent colors

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	30	cm <sup>3</sup> /10min	ISO 1133
Temperature	330	°C	-
Load	2.16	kg	-
<b>ASTM Data</b>			
Melt Flow Index, MFI	33	g/10min	ASTM D 1238
Temperature	330	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	2500	MPa	ISO 527
Yield stress	70	MPa	ISO 527
Yield strain	6	%	ISO 527
Stress at break	60	MPa	ISO 527
Strain at break	50	%	ISO 527
Flexural modulus	2500	MPa	ISO 178
Charpy impact strength, +23°C, 3mm	N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C, 3mm	N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C, 3mm	11	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C, 3mm	9	kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C, 3mm	9	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength, -30°C, 3mm	9	kJ/m <sup>2</sup>	ISO 180/1A
<b>ASTM Data</b>			
Tensile Modulus	2700	MPa	ASTM D 638
Tensile Strength at Yield	70	MPa	ASTM D 638
Tensile Strength at Break	55	MPa	ASTM D 638
Elongation at Yield	6	%	ASTM D 638
Elongation at Break	70	%	ASTM D 638
Flexural Modulus	2600	MPa	ASTM D 790
Izod Impact notched, 1/8 in	97	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	55	J/m	ASTM D 256
Temperature	-30	°C	-

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	152	°C	ISO 75-1/-2
Vicat softening temperature, B	168	°C	ISO 306
Vicat softening temperature, 120°C/h 50N	170	°C	ISO 306
<b>ASTM Data</b>			
DTUL @ 66 psi	166	°C	ASTM D 648
DTUL @ 264 psi	156	°C	ASTM D 648
Vicat Temperature	170	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Water absorption	0.3	%	Sim. to ISO 62
Humidity absorption	0.3	%	Sim. to ISO 62
Density	1200	kg/m <sup>3</sup>	ISO 1183
Density	1210	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	135	°C	-
Pre-drying - Time	4 - 6	h	-
Processing humidity	≤0.02	%	-

**LEXAN™ Copolymer XHT3143T - Europe**

PC

Saudi Basic Industries Corporation (SABIC)

Melt temperature	<b>290 - 325</b>	°C	-
Mold temperature	<b>95 - 130</b>	°C	-
Zone 1	<b>270 - 300</b>	°C	-
Zone 2	<b>280 - 310</b>	°C	-
Zone 3	<b>290 - 325</b>	°C	-
Screw speed	<b>40 - 90</b>	rpm	-
Back pressure	<b>0.3 - 0.7</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

Transparent

**Applications**

Automotive

**Regional Availability**

Europe