

Product Texts

Clear PC-siloxane copolymer with excellent processability, in special light diffusion colors. Medium flow. Improved toughness compared to medium flow standard PC in same color. Color package may affect performance.

UL Yellow Card Link [E45329-512791](https://www.ul.com/yellow-card-link/E45329-512791)

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	9	cm ³ /10min	ISO 1133
Temperature	220	°C	-
Load	5	kg	-
ASTM Data			
Melt Flow Index, MFI	10	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	2310	MPa	ISO 527
Yield stress	57	MPa	ISO 527
Yield strain	5.6	%	ISO 527
Stress at break	58	MPa	ISO 527
Strain at break	50	%	ISO 527
Flexural modulus	2190	MPa	ISO 178
Charpy impact strength, +23°C, 3mm	N	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C, 3mm	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C, 3mm	70	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C, 3mm	60	kJ/m ²	ISO 179/1eA
Izod impact strength, +23°C	N	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 3mm	65	kJ/m ²	ISO 180/1A
Izod notched impact strength, -30°C, 3mm	55	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	2270	MPa	ASTM D 638
Tensile Strength at Yield	60	MPa	ASTM D 638
Tensile Strength at Break	66	MPa	ASTM D 638
Elongation at Yield	6	%	ASTM D 638
Elongation at Break	130	%	ASTM D 638
Flexural Modulus	2270	MPa	ASTM D 790
Izod Impact notched, 1/8 in	890	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	795	J/m	ASTM D 256
Temperature	-30	°C	-
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	119	°C	ISO 75-1/-2
Vicat softening temperature, B	141	°C	ISO 306
Vicat softening temperature, 120°C/h 50N	143	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (GWIT)	825	°C	IEC 60695-2-13
GWIT - thickness tested (3)	3	mm	-
ASTM Data			
DTUL @ 264 psi	124	°C	ASTM D 648
Vicat Temperature	141	°C	ASTM D 1525
Other properties			
Water absorption	0.13	%	Sim. to ISO 62
Humidity absorption	0.09	%	Sim. to ISO 62

LEXAN™ VISUALFX™ Resin FXD1413T - Europe

PC

Saudi Basic Industries Corporation (SABIC)

Density	1190	kg/m ³	ISO 1183
Density	1190	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	295 - 315	°C	-
Mold temperature	70 - 95	°C	-
Zone 1	270 - 295	°C	-
Zone 2	280 - 305	°C	-
Zone 3	295 - 315	°C	-
Screw speed	40 - 70	rpm	-
Back pressure	0.3 - 0.7	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

Europe

Applications

Automotive