

**Product Texts**

Non-chlorinated, non-brominated Flame retardant PC-siloxane copolymer blend. Excellent processability, super high flow, good impact, UL rated V-0. Limited translucent colors.

UL Yellow Card Link [E207780-592770](https://www.ul.com/yellow-card/E207780-592770)

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt volume-flow rate, MVR	29	cm <sup>3</sup> /10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
<b>ASTM Data</b>			
Melt Flow Index, MFI	30	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	2150	MPa	ISO 527
Yield stress	56	MPa	ISO 527
Yield strain	5.6	%	ISO 527
Stress at break	49	MPa	ISO 527
Strain at break	50	%	ISO 527
Flexural modulus	2250	MPa	ISO 178
Charpy notched impact strength, +23°C	49	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C, 4mm	40	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength, -30°C, 4mm	19	kJ/m <sup>2</sup>	ISO 180/1A
<b>ASTM Data</b>			
Tensile Modulus	2200	MPa	ASTM D 638
Tensile Strength at Yield	55	MPa	ASTM D 638
Tensile Strength at Break	50	MPa	ASTM D 638
Elongation at Yield	5.6	%	ASTM D 638
Elongation at Break	100	%	ASTM D 638
Flexural Modulus	2100	MPa	ASTM D 790
Izod Impact notched, 1/8 in	690	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	220	J/m	ASTM D 256
Temperature	-30	°C	-
<b>Thermal properties</b>			
<b>ISO Data</b>			
Vicat softening temperature, B	137	°C	ISO 306
Vicat softening temperature, 120°C/h 50N	138	°C	ISO 306
Burning behav. at thickness h	V-1	class	IEC 60695-11-10
Thickness tested	1.0	mm	-
Glow Wire Flammability Index (GWFI)	875	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (GWIT)	850	°C	IEC 60695-2-13
GWIT - thickness tested (1)	1	mm	-
<b>ASTM Data</b>			
DTUL @ 264 psi	118	°C	ASTM D 648
Vicat Temperature	136	°C	ASTM D 1525
<b>Other properties</b>			
Water absorption	0.26	%	Sim. to ISO 62
Humidity absorption	0.08	%	Sim. to ISO 62
Density	1190	kg/m <sup>3</sup>	ISO 1183
Density	1190	kg/m <sup>3</sup>	ASTM D 792

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>120</b>	°C	-
Pre-drying - Time	<b>3 - 4</b>	h	-
Processing humidity	<b>≤0.02</b>	%	-
Melt temperature	<b>270 - 295</b>	°C	-
Mold temperature	<b>70 - 95</b>	°C	-
Zone 1	<b>250 - 270</b>	°C	-
Zone 2	<b>260 - 280</b>	°C	-
Zone 3	<b>270 - 295</b>	°C	-
Screw speed	<b>40 - 70</b>	rpm	-
Back pressure	<b>0.3 - 0.7</b>	MPa	-

**Characteristics**

**Processing**

Injection Molding

**Special Characteristics**

Flame retardant

**Additives**

Flame retarding agent

**Regional Availability**

Asia Pacific