

Product Texts

LNP COLORCOMP D10008RU compound is based on Polycarbonate (PC) resin. Added features of this grade include: Flame Retardant, Mold Release, UV Stabilized.

UL Yellow Card Link [E121562-103952989](https://www.ul.com/yellowcard/E121562-103952989)

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	7	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	62	MPa	ASTM D 638
Tensile Strength at Break	65	MPa	ASTM D 638
Elongation at Yield	7	%	ASTM D 638
Elongation at Break	110	%	ASTM D 638
Flexural Modulus	2340	MPa	ASTM D 790
Rockwell Hardness	R 118	-	ASTM D 785
Taber Abrasion Resistance	10	mg/1000 cycles	ASTM D 1044
Izod Impact notched, 1/8 in	907	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	3200	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Burning behav. at thickness h	V-2	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
ASTM Data			
Vicat Temperature	154	°C	ASTM D 1525
Thermal Conductivity, solid state	0.0418	W/(m K)	ASTM C 177
Specific Heat	1260	J/(kg K)	ASTM C 351

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Dissipation Factor, 60 Hz	0.0009	-	ASTM D 150
Dissipation Factor, 1 MHz	0.01	-	ASTM D 150
Dielectric Constant, 60 Hz	3.17	-	ASTM D 150
Dielectric Constant, 1 MHz	2.96	-	ASTM D 150
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1200	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	310 - 330	°C	-
Mold temperature	80 - 115	°C	-
Zone 1	290 - 310	°C	-
Zone 2	300 - 320	°C	-
Zone 3	310 - 330	°C	-
Screw speed	40 - 70	rpm	-
Back pressure	0.3 - 0.7	MPa	-

Characteristics

Processing

Injection Molding

Applications

Automotive

Additives

Flame retarding agent

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

Flame retardant