

Product Texts

LNP COLORCOMP DX06407 compound is based on Polycarbonate (PC) resin. Added features of this grade include: Easy Molding, Good Mold Release, Healthcare.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.8	mm/mm	ASTM D 955
Mold Shrinkage, TD	2	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2300	MPa	ISO 527
Yield stress	65	MPa	ISO 527
Yield strain	6.3	%	ISO 527
Stress at break	54	MPa	ISO 527
Strain at break	50	%	ISO 527
Flexural modulus	2290	MPa	ISO 178
Flexural strength	91	MPa	ISO 178
Izod impact strength, +23°C, 4mm	224	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	9	kJ/m ²	ISO 180/1A

ASTM Data			
Tensile Modulus	2340	MPa	ASTM D 638
Tensile Strength at Yield	63	MPa	ASTM D 638
Tensile Strength at Break	58	MPa	ASTM D 638
Elongation at Yield	6.2	%	ASTM D 638
Elongation at Break	94	%	ASTM D 638
Flexural Modulus	2400	MPa	ASTM D 790
Izod Impact notched, 1/8 in	781	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	1310	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	96	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	104	°C	ISO 75-1/-2
ASTM Data			
DTUL @ 66 psi	103	°C	ASTM D 648
DTUL @ 264 psi	94	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1200	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	305 - 325	°C	-
Mold temperature	80 - 110	°C	-
Zone 1	295 - 305	°C	-
Zone 2	310 - 320	°C	-
Zone 3	320 - 330	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific