

Product Texts

LNP ELCRES CRX9411U is an UV stabilized, amorphous Polycarbonate (PC) copolymer resin that offers medium flow, with UL Electrical and V0 rating @ 1.6 mm for all colors, and high ductility in combination with excellent chemical resistance. This grade is available for custom coloring and may be an excellent candidate for a wide variety of applications that need improved chemical resistance.

UL Yellow Card [E121562-104571194](https://www.ul.com/yellow-card/E121562-104571194)

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	9	cm ³ /10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
ASTM Data			
Melt Flow Index, MFI	10	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.0065	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.0065	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1860	MPa	ISO 527
Yield stress	50	MPa	ISO 527
Yield strain	6	%	ISO 527
Stress at break	57	MPa	ISO 527
Strain at break	100	%	ISO 527
Flexural modulus, 23°C	2010	MPa	ISO 178
Flexural strength	80	MPa	ISO 178
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	65	kJ/m ²	ISO 179/1eA
Izod impact strength, +23°C	N	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	55	kJ/m ²	ISO 180/1A
Izod notched impact strength	35	kJ/m ²	ISO 180/1A
Temperature	-70	°C	-
ASTM Data			
Tensile Modulus	1920	MPa	ASTM D 638
Tensile Strength at Yield	52	MPa	ASTM D 638
Tensile Strength at Break	59	MPa	ASTM D 638
Elongation at Yield	6	%	ASTM D 638
Elongation at Break	100	%	ASTM D 638
Flexural Modulus	2000	MPa	ASTM D 790
Flexural Strength	85	MPa	ASTM D 790
Izod Impact notched, 1/8 in	756	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	680	J/m	ASTM D 256
Temperature	-30	°C	-
Izod Impact unnotched, 1/8 in	N	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	123	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	137	°C	ISO 75-1/-2
Vicat softening temperature, B	142	°C	ISO 306
Coeff. of linear therm. expansion, parallel	70	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	70	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Yellow Card available	yes	-	-

ASTM Data

Coefficient of Thermal Expansion, MD	70	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	70	E-6/K	ASTM D 696
DTUL @ 66 psi	138	°C	ASTM D 648
DTUL @ 264 psi	125	°C	ASTM D 648
Vicat Temperature	142	°C	ASTM D 1525

Electrical properties

	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	1E13	Ohm	ASTM D 257
Volume Resistivity	1E15	Ohm*cm	ASTM D 257

Other properties

	Value	Unit	Test Standard
Humidity absorption	0.08	%	Sim. to ISO 62
Density	1190	kg/m ³	ISO 1183
Density	1200	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding

	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	290 - 340	°C	-
Mold temperature	80 - 110	°C	-
Zone 1	270 - 320	°C	-
Zone 2	280 - 330	°C	-
Zone 3	290 - 340	°C	-
Nozzle temperature	80 - 110	°C	-
Screw speed	50 - 100	rpm	-
Back pressure	0.3 - 0.7	MPa	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Flame retardant, High impact or impact modified, U.V. stabilized or stable to weather

Features

Amorphous, Ductile, Copolymer

Chemical Resistance

General Chemical Resistance

Applications

Medical, Packaging

Regional Availability

North America, Europe, Asia Pacific, South and Central America