

**Product Texts**

LNP ELCRES EXL1418TAML is a polycarbonate (PC) siloxane copolymer containing antimicrobial additives, medium flow, transparent and injection molding (IM) grade, available in transparent or tinted colors. This resin offers room temperature ductility in combination with excellent processability and release with opportunities for shorter IM cycle times compared with standard PC.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	8.7	cm <sup>3</sup> /10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
<b>ASTM Data</b>			
Melt Flow Index, MFI	9	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.006	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	2040	MPa	ISO 527
Yield stress	54	MPa	ISO 527
Yield strain	5.6	%	ISO 527
Stress at break	51	MPa	ISO 527
Strain at break	85.6	%	ISO 527
Flexural modulus, 23°C	2170	MPa	ISO 178
Flexural strength	75	MPa	ISO 178
Charpy impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	38	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	13	kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	41	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	14	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-30	°C	-
<b>ASTM Data</b>			
Tensile Modulus	2070	MPa	ASTM D 638
Tensile Strength at Yield	54	MPa	ASTM D 638
Tensile Strength at Break	57	MPa	ASTM D 638
Elongation at Yield	5	%	ASTM D 638
Elongation at Break	104	%	ASTM D 638
Flexural Modulus	2080	MPa	ASTM D 790
Flexural Strength	84	MPa	ASTM D 790
Izod Impact notched, 1/8 in	530	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	138	J/m	ASTM D 256
Temperature	-30	°C	-

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	118	°C	ISO 75-1/-2
Vicat softening temperature, B	143	°C	ISO 306
Coeff. of linear therm. expansion, parallel	67	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	80	E-6/K	ISO 11359-1/-2
<b>ASTM Data</b>			
Coefficient of Thermal Expansion, MD	67	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	80	E-6/K	ASTM D 696
DTUL @ 264 psi	119	°C	ASTM D 648
Vicat Temperature	143	°C	ASTM D 1525

Optical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Haze	11	%	ASTM D 1003
Light Transmittance	89.8	%	ASTM D 1003

Other properties	Value	Unit	Test Standard
Water absorption	0.12	%	Sim. to ISO 62
Humidity absorption	0.09	%	Sim. to ISO 62
Density	1180	kg/m <sup>3</sup>	ISO 1183
Density	1180	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	295 - 315	°C	-
Mold temperature	70 - 95	°C	-
Zone 1	270 - 295	°C	-
Zone 2	280 - 305	°C	-
Zone 3	295 - 315	°C	-
Nozzle temperature	290 - 310	°C	-

## Characteristics

### Processing

Injection Molding

### Additives

Release agent

### Special Characteristics

High impact or impact modified, Transparent

### Features

Ductile, Copolymer

### Applications

Aircraft and Aerospace, Automotive, Building Construction, IT / Business Machine, Electrical and Electronical, Medical, Refrigeration

### Regional Availability

North America, Europe, Asia Pacific, South and Central America