

Product Texts

ELCRIN EXL9330B polycarbonate (PC) siloxane copolymer resin is a UV stabilized high flow opaque injection molding (IM) grade with major component synthesized from Bio source. This resin offers UL94 V0 @1.5mm flame retardancy based on non-bromine, non-chlorine FR systems, extreme low temperature ductility (-60°C) characteristics and excellent processability with opportunities for shorter IM cycle times compared to standard PC. ELCRIN EXL9330B resin is a product available in a wide range of opaque colors and may be an excellent candidate for a wide range of applications.

UL Yellow Card [E207780-102516601](#)

UL Yellow Card [E207780-228378](#)

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	9	cm ³ /10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
ASTM Data			
Melt Flow Index, MFI	10	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.006	mm/mm	ASTM D 955
Mechanical properties			
ISO Data			
Tensile Modulus	2100	MPa	ISO 527
Yield stress	55	MPa	ISO 527
Yield strain	6	%	ISO 527
Stress at break	60	MPa	ISO 527
Strain at break	125	%	ISO 527
Flexural modulus, 23°C	2200	MPa	ISO 178
Flexural strength	85	MPa	ISO 178
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	75	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	60	kJ/m ²	ISO 179/1eA
Izod impact strength, +23°C	N	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	70	kJ/m ²	ISO 180/1A
Izod notched impact strength	55	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-
Ball indentation hardness	90	MPa	ISO 2039-1
ASTM Data			
Tensile Modulus	2100	MPa	ASTM D 638
Tensile Strength at Yield	58	MPa	ASTM D 638
Tensile Strength at Break	61	MPa	ASTM D 638
Elongation at Yield	6	%	ASTM D 638
Elongation at Break	130	%	ASTM D 638
Flexural Modulus	2060	MPa	ASTM D 790
Flexural Strength	88	MPa	ASTM D 790
Izod Impact notched, 1/8 in	801	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	587	J/m	ASTM D 256
Temperature	-50	°C	-
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	124	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	135	°C	ISO 75-1/-2
Vicat softening temperature, B	140	°C	ISO 306

Coeff. of linear therm. expansion, parallel	72	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	77	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.6	mm	-
Yellow Card available	yes	-	-
Burning behav. 5V at thickness h	5VB	class	IEC 60695-11-20
Thickness tested	2.5	mm	-
Yellow Card available	yes	-	-
Oxygen index	35	%	ISO 4589-1/-2
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (1)	1	mm	-
Glow Wire Ignition Temperature (GWIT)	825	°C	IEC 60695-2-13
GWIT - thickness tested (1)	1	mm	-
ASTM Data			
UL 94 Flame rating	V-1	-	UL 94
Thickness tested	0.8	mm	-
Coefficient of Thermal Expansion, MD	66.6	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	66.6	E-6/K	ASTM D 696
DTUL @ 66 psi	134	°C	ASTM D 648
DTUL @ 264 psi	120	°C	ASTM D 648
Vicat Temperature	142	°C	ASTM D 1525

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	16	kV/mm	IEC 60243-1
Comparative tracking index	225	-	IEC 60112
ASTM Data			
Dielectric Strength, Short Time	17	kV/mm	ASTM D 149

Other properties	Value	Unit	Test Standard
Water absorption	0.35	%	Sim. to ISO 62
Humidity absorption	0.15	%	Sim. to ISO 62
Density	1190	kg/m ³	ISO 1183
Density	1180	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	295 - 315	°C	-
Mold temperature	70 - 95	°C	-
Zone 1	275 - 295	°C	-
Zone 2	280 - 305	°C	-
Zone 3	295 - 315	°C	-
Nozzle temperature	290 - 310	°C	-
Screw speed	40 - 70	rpm	-
Back pressure	0.3 - 0.7	MPa	-

Characteristics

Processing

Injection Molding

Certifications

Contains renewable resources

Special Characteristics

Flame retardant, Halogen-free, High impact or impact modified, U.V. stabilized or stable to weather, Opaque

Features

Ductile, Copolymer

Applications

IT / Business Machine, Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America