

Product Texts

LNP STAT-KON DX11411R compound is based on Polycarbonate (PC) resin containing proprietary fillers. Added features of this grade include: Electrically Conductive, Radar Absorbing.

UL Yellow Card Link [E121562-103811086](https://www.ulprospector.com/121562-103811086)

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, normal	0.5	%	ISO 294-4, 2577
ASTM Data			
Mold Shrinkage, MD	0.3	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	6950	MPa	ISO 527
Stress at break	85	MPa	ISO 527
Strain at break	1.5	%	ISO 527
Flexural modulus	6420	MPa	ISO 178
Flexural strength	114	MPa	ISO 178
Izod impact strength, +23°C, 4mm	20	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	5	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	7270	MPa	ASTM D 638
Tensile Strength at Break	87	MPa	ASTM D 638
Elongation at Break	1.5	%	ASTM D 638
Flexural Modulus	6780	MPa	ASTM D 790
Izod Impact notched, 1/8 in	58	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	284	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	144	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	152	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
ASTM Data			
Coefficient of Thermal Expansion, MD	31	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	47	E-6/K	ASTM D 696
DTUL @ 66 psi	153	°C	ASTM D 648
DTUL @ 264 psi	144	°C	ASTM D 648

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	100000	Ohm	ASTM D 257

Other properties	Value	Unit	Test Standard
Humidity absorption	0.2	%	Sim. to ISO 62
Water Absorption, 24hr	0.26	%	ASTM D 570
Density	1400	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	305 - 325	°C	-
Mold temperature	80 - 110	°C	-
Zone 1	295 - 305	°C	-
Zone 2	310 - 320	°C	-

Zone 3	320 - 330	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics**Processing**

Injection Molding

Applications

Automotive

Special Characteristics

Increased electrical conductivity

Regional Availability

North America, Europe, Asia Pacific