

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.007	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2410	MPa	ASTM D 638
Tensile Strength at Break	48.3	MPa	ASTM D 638
Elongation at Break	7	%	ASTM D 638
Flexural Modulus	2410	MPa	ASTM D 790
Flexural Strength	75.8	MPa	ASTM D 790
Izod Impact notched, 1/4 in	100	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1280	kg/m ³	ASTM D 792

Characteristics

Delivery form
Pellets

Applications
IT / Business Machine

Additives
Lubricants

Regional Availability
Europe, Asia Pacific, South and Central America, Near East/Africa