

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>22</b>	g/10min	ASTM D 1238
Temperature	<b>300</b>	°C	-
Load	<b>1.2</b>	kg	-
Mold Shrinkage, MD	<b>0.006</b>	mm/mm	ASTM D 955

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>61.8</b>	MPa	ASTM D 638
Elongation at Break	<b>100</b>	%	ASTM D 638
Flexural Modulus	<b>2256</b>	MPa	ASTM D 790
Flexural Strength	<b>91.2</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 118</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>660</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-2</b>	-	UL 94
Thickness tested	<b>1.5</b>	mm	-
DTUL @ 264 psi	<b>130</b>	°C	ASTM D 648
Vicat Temperature	<b>141</b>	°C	ASTM D 1525

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Volume Resistivity	<b>2E15</b>	Ohm*cm	ASTM D 257

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1210</b>	kg/m <sup>3</sup>	ASTM D 792

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>100 - 120</b>	°C	-
Pre-drying - Time	<b>3 - 5</b>	h	-
Processing humidity	<b>≤0.02</b>	%	-
Melt temperature	<b>300 - 320</b>	°C	-
Mold temperature	<b>80 - 120</b>	°C	-
Zone 1	<b>260 - 280</b>	°C	-
Zone 2	<b>280 - 300</b>	°C	-
Zone 3	<b>300 - 320</b>	°C	-
Nozzle temperature	<b>300 - 320</b>	°C	-
Screw speed	<b>40 - 70</b>	rpm	-
Back pressure	<b>1 - 4</b>	MPa	-

**Characteristics**

**Processing**

Injection Molding

**Special Characteristics**

Flame retardant, Halogen-free, Transparent

**Applications**

IT / Business Machine, Electrical and Electronical

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America