

**Product Texts**

- (PC ABS)-Blend
- flame retardant
- easy flowing
- Vicat/B 120 temperature = 110 °C
- increased heat resistance
- UL recognition 94 V-0 at 1.5 mm

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	<b>29</b>	cm³/10min	ISO 1133
Temperature	<b>240</b>	°C	-
Load	<b>5</b>	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>2600</b>	MPa	ISO 527
<sup>[C]</sup> Yield stress	<b>60</b>	MPa	ISO 527
<sup>[C]</sup> Yield strain	<b>4</b>	%	ISO 527

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>91</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	<b>101</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	<b>108</b>	°C	ISO 306
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	<b>68</b>	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	<b>68</b>	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	<b>V-0</b>	class	IEC 60695-11-10
Thickness tested	<b>1.5</b>	mm	-

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Relative permittivity, 100Hz	<b>3.2</b>	-	IEC 62631-2-1
<sup>[C]</sup> Relative permittivity, 1MHz	<b>3.1</b>	-	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 100Hz	<b>50</b>	E-4	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 1MHz	<b>70</b>	E-4	IEC 62631-2-1
<sup>[C]</sup> Volume resistivity	<b>&gt;1E13</b>	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	<b>&gt;1E15</b>	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	<b>30</b>	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	<b>350</b>	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Water absorption	<b>0.5</b>	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	<b>0.2</b>	%	Sim. to ISO 62
<sup>[C]</sup> Density	<b>1180</b>	kg/m³	ISO 1183

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Injection Molding, melt temperature	<b>240</b>	°C	ISO 294
Injection Molding, mold temperature	<b>80</b>	°C	ISO 294
Injection Molding, injection velocity	<b>240</b>	mm/s	ISO 294

[C]: CAMPUS

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>75 - 100</b>	°C	-
Pre-drying - Time	<b>2 - 4</b>	h	-
Processing humidity	<b>≤0.02</b>	%	-
Melt temperature	<b>240 - 280</b>	°C	-
Mold temperature	<b>70 - 100</b>	°C	-

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

Flame retardant

**Delivery form**

Pellets

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

**Additives**

Release agent

**Other text information****Injection molding**

## PREPROCESSING

Max. Water content: 0.02 %

Drying temperature: 75 - 100 °C

(depending on the grade 10°C below the Vicat VST/B120 temperature, but not higher as the recommended values).

Drying time:

Circulating air drying oven (50 % fresh air) 4-8 h

Fresh air dryer (high speed dryer) 2-4 h

Dry air dryer 2-4 h

## PROCESSING

Melt temperature: 240-280 °C

Mold temperature: 70-100 °C

Use open nozzle.