

**Product Texts**

- MVR (300 °C/1.2 kg) 19 cm³/10 min
- food contact quality
- low viscosity
- easy release

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	19	cm³/10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
<sup>[C]</sup> Molding shrinkage, parallel	0.7	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	0.7	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	2400	MPa	ISO 527
<sup>[C]</sup> Yield stress	65	MPa	ISO 527
<sup>[C]</sup> Yield strain	6.2	%	ISO 527
<sup>[C]</sup> Nominal strain at break	>50	%	ISO 527
<sup>[C]</sup> Tensile creep modulus, 1h	2200	MPa	ISO 899-1
<sup>[C]</sup> Tensile creep modulus, 1000h	1900	MPa	ISO 899-1
<sup>[C]</sup> Charpy impact strength, +23°C	N	kJ/m²	ISO 179/1eU
<sup>[C]</sup> Puncture - maximum force, +23°C	5100	N	ISO 6603-2
<sup>[C]</sup> Puncture - maximum force, -30°C	6000	N	ISO 6603-2
<sup>[C]</sup> Puncture energy, +23°C	55	J	ISO 6603-2
<sup>[C]</sup> Puncture energy, -30°C	65	J	ISO 6603-2

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Glass transition temperature, 10°C/min	146	°C	ISO 11357-1/-2
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	125	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	138	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	145	°C	ISO 306
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	65	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	65	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at thickness h	V-2	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
<sup>[C]</sup> Oxygen index	28	%	ISO 4589-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Relative permittivity, 100Hz	3.1	-	IEC 62631-2-1
<sup>[C]</sup> Relative permittivity, 1MHz	3	-	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 100Hz	5	E-4	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 1MHz	90	E-4	IEC 62631-2-1
<sup>[C]</sup> Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	>1E15	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	34	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	250	-	IEC 60112

[C]: CAMPUS

Optical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Luminous transmittance	89	%	ISO 13468-1, -2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Water absorption	<b>0.3</b>	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	<b>0.12</b>	%	Sim. to ISO 62
<sup>[C]</sup> Density	<b>1200</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Injection Molding, melt temperature	<b>280</b>	°C	ISO 294
Injection Molding, mold temperature	<b>80</b>	°C	ISO 294
Injection Molding, injection velocity	<b>200</b>	mm/s	ISO 294

[C]: CAMPUS

**Characteristics**

**Special Characteristics**

Transparent

**Regional Availability**

North America, Europe, Asia Pacific, Near East/Africa

**Certifications**

Contains renewable resources, Food contact, ISCC Plus