

**Product Texts**

- MVR (300 °C/1.2 kg) 14 cm<sup>3</sup>/10 min
- medical devices
- suitable for ETO and steam sterilization at 121 °C
- biocompatible according to many ISO 10993-1 test requirements
- medium viscosity
- easy release

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	<b>14</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>300</b>	°C	-
Load	<b>1.2</b>	kg	-
<sup>[C]</sup> Molding shrinkage, parallel	<b>0.7</b>	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	<b>0.7</b>	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>2400</b>	MPa	ISO 527
<sup>[C]</sup> Yield stress	<b>66</b>	MPa	ISO 527
<sup>[C]</sup> Yield strain	<b>6.1</b>	%	ISO 527
<sup>[C]</sup> Nominal strain at break	<b>&gt;50</b>	%	ISO 527
<sup>[C]</sup> Tensile creep modulus, 1h	<b>2200</b>	MPa	ISO 899-1
<sup>[C]</sup> Tensile creep modulus, 1000h	<b>1900</b>	MPa	ISO 899-1
<sup>[C]</sup> Charpy impact strength, +23°C	<b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	<b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Puncture - maximum force, +23°C	<b>5400</b>	N	ISO 6603-2
<sup>[C]</sup> Puncture - maximum force, -30°C	<b>6300</b>	N	ISO 6603-2
<sup>[C]</sup> Puncture energy, +23°C	<b>60</b>	J	ISO 6603-2
<sup>[C]</sup> Puncture energy, -30°C	<b>65</b>	J	ISO 6603-2

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Glass transition temperature, 10°C/min	<b>144</b>	°C	ISO 11357-1/-2
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>124</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	<b>136</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	<b>144</b>	°C	ISO 306
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	<b>65</b>	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	<b>65</b>	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Oxygen index	<b>28</b>	%	ISO 4589-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Relative permittivity, 100Hz	<b>3.1</b>	-	IEC 62631-2-1
<sup>[C]</sup> Relative permittivity, 1MHz	<b>3</b>	-	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 100Hz	<b>5</b>	E-4	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 1MHz	<b>90</b>	E-4	IEC 62631-2-1
<sup>[C]</sup> Volume resistivity	<b>&gt;1E13</b>	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	<b>&gt;1E15</b>	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	<b>34</b>	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	<b>250</b>	-	IEC 60112

[C]: CAMPUS

Optical properties	Value	Unit	Test Standard
<b>ISO Data</b>			

[C] Luminous transmittance	89	%	ISO 13468-1, -2
[C]: CAMPUS			

Other properties	Value	Unit	Test Standard
[C] Water absorption	0.3	%	Sim. to ISO 62
[C] Humidity absorption	0.12	%	Sim. to ISO 62
[C] Density	1200	kg/m <sup>3</sup>	ISO 1183
[C]: CAMPUS			

Test specimen production	Value	Unit	Test Standard
<b>ISO Data</b>			
[C] Injection Molding, melt temperature	290	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294
[C]: CAMPUS			

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	2 - 3	h	-
Processing humidity	≤0.02	%	-
Melt temperature	280 - 320	°C	-
Mold temperature	80 - 100	°C	-

## Characteristics

### Processing

Injection Molding

### Delivery form

Pellets

### Additives

Release agent

### Special Characteristics

Transparent, Opaque, Sterilizable, Ethylene Oxide (EtO)  
Sterilization, Steam sterilization, Gamma irradiation sterilization

### Certifications

Medical Grade, Biocompatibility ISO 10993, US Pharmacopeia  
Class VI Approved

### Applications

Medical

### Regional Availability

North America, Europe, Asia Pacific, South and Central America,  
Near East/Africa

## Other text information

### Injection molding

#### PREPROCESSING

Max. Water content: 0.01 - 0.02 %

Drying temperature: 120 °C

Drying time:

Circulating air drying oven (50 % fresh air) 4-8 h

Fresh air dryer (high speed dryer) 2-4 h

Dry air dryer 2-3 h

#### PROCESSING

Melt temperature: 280-320 °C

Mold temperature: 80-100 °C

Use open nozzle.