

**Product Texts**

- medium viscosity
- easy release
- UV stabilized
- UV 400 cut off
- optical lenses

**Processing/Physical Characteristics**

	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	8.5	cm <sup>3</sup> /10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-

[C]: CAMPUS

**Mechanical properties**

	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	2300	MPa	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 179/1eU

[C]: CAMPUS

**Test specimen production**

	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Injection Molding, melt temperature	80	°C	ISO 294
Injection Molding, mold temperature	290	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294

[C]: CAMPUS

**Characteristics****Special Characteristics**

U.V. stabilized or stable to weather

**Regional Availability**

North America, Europe, Asia Pacific, Near East/Africa

**Certifications**

Contains renewable resources, ISCC Plus