

Product Texts

- MVR (300 °C/1.2 kg) 15 cm³/10 min
- medical devices
- suitable for sterilization with high-energy radiation
- biocompatible according to many ISO 10993-1 test requirements
- medium viscosity
- transparent parts for medical devices

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|-------------|------------------------|-----------------|
| ISO Data | | | |
| ^[C] Melt volume-flow rate, MVR | 15 | cm ³ /10min | ISO 1133 |
| Temperature | 300 | °C | - |
| Load | 1.2 | kg | - |
| Melt flow index, MFI | 15.5 | g/10min | ISO 1133 |
| Temperature | 300 | °C | - |
| Load | 1.2 | kg | - |
| ^[C] Molding shrinkage, parallel | 0.6 | % | ISO 294-4, 2577 |
| ^[C] Molding shrinkage, normal | 0.7 | % | ISO 294-4, 2577 |

[C]: CAMPUS

| Mechanical properties | Value | Unit | Test Standard |
|--|---------------|-------------------|---------------|
| ISO Data | | | |
| ^[C] Tensile Modulus | 2400 | MPa | ISO 527 |
| ^[C] Yield stress | 67 | MPa | ISO 527 |
| ^[C] Yield strain | 6.1 | % | ISO 527 |
| ^[C] Nominal strain at break | >50 | % | ISO 527 |
| Flexural modulus, 23°C | 2400 | MPa | ISO 178 |
| Flexural strength | 100 | MPa | ISO 178 |
| ^[C] Charpy impact strength, +23°C | N | kJ/m ² | ISO 179/1eU |
| Charpy notched impact strength, +23°C, 3mm | 70 | kJ/m ² | ISO 179/1eA |
| Type of failure | P | - | - |
| Charpy notched impact strength, -30°C, 3mm | 14 | kJ/m ² | ISO 179/1eA |
| Type of failure | C | - | - |
| Izod notched impact strength, +23°C | 65 | kJ/m ² | ISO 180/1A |
| Izod notched impact strength | 12 | kJ/m ² | ISO 180/1A |
| Temperature | -30 | °C | - |
| ^[C] Puncture - maximum force, +23°C | 5300 | N | ISO 6603-2 |
| ^[C] Puncture - maximum force, -30°C | 6200 | N | ISO 6603-2 |
| ^[C] Puncture energy, +23°C | 60 | J | ISO 6603-2 |
| ^[C] Puncture energy, -30°C | 70 | J | ISO 6603-2 |
| Ball indentation hardness | 118 | MPa | ISO 2039-1 |

[C]: CAMPUS

| Thermal properties | Value | Unit | Test Standard |
|--|------------|-------|----------------|
| ISO Data | | | |
| ^[C] Glass transition temperature, 10°C/min | 142 | °C | ISO 11357-1/-2 |
| ^[C] Temp. of deflection under load, 1.80 MPa | 122 | °C | ISO 75-1/-2 |
| ^[C] Temp. of deflection under load, 0.45 MPa | 134 | °C | ISO 75-1/-2 |
| ^[C] Vicat softening temperature, B | 141 | °C | ISO 306 |
| ^[C] Coeff. of linear therm. expansion, parallel | 65 | E-6/K | ISO 11359-1/-2 |
| ^[C] Coeff. of linear therm. expansion, normal | 65 | E-6/K | ISO 11359-1/-2 |
| ^[C] Oxygen index | 27 | % | ISO 4589-1/-2 |

[C]: CAMPUS

| Electrical properties | Value | Unit | Test Standard |
|------------------------------------|-----------------|-------|---------------|
| ISO Data | | | |
| ^[C] Volume resistivity | >1E13 | Ohm*m | IEC 62631-3-1 |
| ^[C] Surface resistivity | >1E15 | Ohm | IEC 62631-3-2 |

[C]: CAMPUS

| Other properties | Value | Unit | Test Standard |
|------------------------------------|-------------|-------------------|----------------|
| ^[C] Water absorption | 0.3 | % | Sim. to ISO 62 |
| ^[C] Humidity absorption | 0.12 | % | Sim. to ISO 62 |
| ^[C] Density | 1200 | kg/m ³ | ISO 1183 |
| Bulk density | 660 | kg/m ³ | - |

[C]: CAMPUS

| Test specimen production | Value | Unit | Test Standard |
|--|------------|------|---------------|
| ISO Data | | | |
| ^[C] Injection Molding, melt temperature | 280 | °C | ISO 294 |
| Injection Molding, mold temperature | 80 | °C | ISO 294 |
| Injection Molding, injection velocity | 200 | mm/s | ISO 294 |

[C]: CAMPUS

| Processing Recommendation Injection Molding | Value | Unit | Test Standard |
|---|------------------|------|---------------|
| Pre-drying - Temperature | 120 | °C | - |
| Pre-drying - Time | 2 - 3 | h | - |
| Processing humidity | ≤0.02 | % | - |
| Melt temperature | 280 - 320 | °C | - |
| Mold temperature | 80 - 120 | °C | - |
| Zone 1 | 250 - 260 | °C | - |
| Zone 2 | 270 - 280 | °C | - |
| Zone 3 | 280 - 290 | °C | - |
| Nozzle temperature | 290 - 300 | °C | - |
| Back pressure | 5 - 15 | MPa | - |

Characteristics

Processing

Injection Molding

Special Characteristics

Transparent, Sterilizable, Gamma irradiation sterilization

Chemical Resistance

Radiation Resistance

Certifications

Contains renewable resources, Medical Grade, Biocompatibility ISO 10993, ISCC Plus

Applications

Medical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa