

Matrixx 50N5006

PC

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	10	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data	Value	Unit	Test Standard
Tensile Strength at Yield	62.1	MPa	ASTM D 638
Flexural Modulus	2340	MPa	ASTM D 790
Gardner Impact	36.2	J	ASTM D 2794,4226,5420
Izod Impact notched, 1/8 in	690	J/m	ASTM D 256
Thermal properties			
ASTM Data	Value	Unit	Test Standard
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 66 psi	129	°C	ASTM D 648
DTUL @ 264 psi	127	°C	ASTM D 648
Other properties			
Value	Unit	Test Standard	
Density	1200	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Pellets

Regional Availability

North America