

ML3000

PC

Cheng Yu Plastic Company Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	17.5	g/10min	ASTM D 1238
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength	60	MPa	ASTM D 638
Flexural Strength	90	MPa	ASTM D 790
Rockwell Hardness	R 120	-	ASTM D 785
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	1.5	mm	-
Other properties			
Density	1200	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

High impact or impact modified

Regional Availability

Asia Pacific

Applications

Electrical and Electrical, General Purpose