

Nemcon™ H PC DP184

PC

Ovation Polymers

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	7810	MPa	ASTM D 638
Tensile Strength at Break	55	MPa	ASTM D 638
Elongation at Break	2	%	ASTM D 638
Flexural Modulus	6750	MPa	ASTM D 790
Izod Impact notched, 1/8 in	133	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1620	kg/m ³	ASTM D 792

Characteristics**Regional Availability**

North America