

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	28	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.0065	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
Value	Unit	Test Standard	
<b>ASTM Data</b>			
Tensile Strength at Yield	60	MPa	ASTM D 638
Tensile Strength at Break	55	MPa	ASTM D 638
Flexural Modulus	2300	MPa	ASTM D 790
Flexural Strength	80	MPa	ASTM D 790
Rockwell Hardness	R 60	-	ASTM D 785
Izod Impact notched, 1/8 in	336	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	96.1	J/m	ASTM D 256
Temperature	-20	°C	-
<b>Thermal properties</b>			
Value	Unit	Test Standard	
<b>ISO Data</b>			
Coeff. of linear therm. expansion, normal	70	E-6/K	ISO 11359-1/-2
<b>ASTM Data</b>			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	1.6	mm	-
DTUL @ 264 psi	125	°C	ASTM D 648
Vicat Temperature	145	°C	ASTM D 1525
<b>Electrical properties</b>			
Value	Unit	Test Standard	
<b>ISO Data</b>			
Relative permittivity, 1MHz	3	-	IEC 62631-2-1
Dissipation factor, 1MHz	90	E-4	IEC 62631-2-1
Volume resistivity	1E12	Ohm*m	IEC 62631-3-1
Surface resistivity	1E15	Ohm	IEC 62631-3-2
Electric strength	25	kV/mm	IEC 60243-1
<b>Other properties</b>			
Value	Unit	Test Standard	
Water absorption	0.3	%	Sim. to ISO 62
Humidity absorption	0.12	%	Sim. to ISO 62
Density	1200	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Processing

Injection Molding

### Additives

Release agent

### Applications

General Purpose

### Regional Availability

Europe