

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	8	cm <sup>3</sup> /10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
Value	Unit	Test Standard	
<b>ISO Data</b>			
Tensile Modulus	2400	MPa	ISO 527
Yield stress	61	MPa	ISO 527
Yield strain	6	%	ISO 527
Nominal strain at break	>50	%	ISO 527
Stress at break	54	MPa	ISO 527
Flexural modulus, 23°C	2100	MPa	ISO 178
Flexural strength	93	MPa	ISO 178
Charpy impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	65	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
Value	Unit	Test Standard	
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	129	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	70	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	70	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-2	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Burning behav. at thickness h	V-2	class	IEC 60695-11-10
Thickness tested	0.4	mm	-
Glow Wire Flammability Index (GWFI)	850	°C	IEC 60695-2-12
GWFI - thickness tested (1)	1.5	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (2)	3	mm	-
Glow Wire Ignition Temperature (GWIT)	875	°C	IEC 60695-2-13
GWIT - thickness tested (1)	1.5	mm	-
Glow Wire Ignition Temperature (GWIT)	875	°C	IEC 60695-2-13
GWIT - thickness tested (2)	3	mm	-
<b>ASTM Data</b>			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	3	mm	-
<b>Electrical properties</b>			
Value	Unit	Test Standard	
<b>ISO Data</b>			
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
<b>Optical properties</b>			
Value	Unit	Test Standard	
<b>ASTM Data</b>			
Light Transmittance	52	%	ASTM D 1003
<b>Other properties</b>			
Value	Unit	Test Standard	
Density	1200	kg/m <sup>3</sup>	ISO 1183
<b>Processing Recommendation Extrusion</b>			
Value	Unit	Test Standard	
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	5 - 8	h	-
Melt temperature	270 - 320	°C	-

Nozzle temperature

**270 - 320**

°C

-

**Characteristics**

**Processing**

Other Extrusion

**Delivery form**

Pellets, White

**Special Characteristics**

Flame retardant, U.V. stabilized or stable to weather

**Features**

Light Diffusing

**Applications**

Electrical and Electronical

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa