

Panlite® MN-4800

PC

Teijin Chemicals Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Yield stress	63	MPa	ISO 527
Nominal strain at break	>50	%	ISO 527
Flexural modulus, 23°C	2260	MPa	ISO 178
Flexural strength	98	MPa	ISO 178
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	10	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	125	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	70	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	70	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (1)	1.5	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (2)	2	mm	-
Glow Wire Ignition Temperature (GWIT)	850	°C	IEC 60695-2-13
GWIT - thickness tested (1)	1.5	mm	-
Glow Wire Ignition Temperature (GWIT)	850	°C	IEC 60695-2-13
GWIT - thickness tested (2)	2	mm	-
Electrical properties			
ISO Data			
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Optical properties			
ASTM Data			
Light Transmittance	88	%	ASTM D 1003
Other properties			
Density	1200	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	5 - 8	h	-
Melt temperature	270 - 320	°C	-
Mold temperature	80 - 120	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Special Characteristics

Flame retardant, Halogen-free, Transparent

Applications

Electrical and Electronical, General Purpose

Additives

Release agent

Regional Availability

North America, Europe, Asia Pacific, South and Central America,
Near East/Africa